



Tensile Properties and Microstructural Characterization of Hi-Nicalon SiC/RBSN Composites

Ramakrishna T. Bhatt

U.S. Army Research Laboratory, Lewis Research Center, Cleveland, Ohio

The NASA STI Program Office . . . in Profile

Since its founding, NASA has been dedicated to the advancement of aeronautics and space science. The NASA Scientific and Technical Information (STI) Program Office plays a key part in helping NASA maintain this important role.

The NASA STI Program Office is operated by Langley Research Center, the Lead Center for NASA's scientific and technical information. The NASA STI Program Office provides access to the NASA STI Database, the largest collection of aeronautical and space science STI in the world. The Program Office is also NASA's institutional mechanism for disseminating the results of its research and development activities. These results are published by NASA in the NASA STI Report Series, which includes the following report types:

- **TECHNICAL PUBLICATION.** Reports of completed research or a major significant phase of research that present the results of NASA programs and include extensive data or theoretical analysis. Includes compilations of significant scientific and technical data and information deemed to be of continuing reference value. NASA's counterpart of peer-reviewed formal professional papers but has less stringent limitations on manuscript length and extent of graphic presentations.
- **TECHNICAL MEMORANDUM.** Scientific and technical findings that are preliminary or of specialized interest, e.g., quick release reports, working papers, and bibliographies that contain minimal annotation. Does not contain extensive analysis.
- **CONTRACTOR REPORT.** Scientific and technical findings by NASA-sponsored contractors and grantees.

- **CONFERENCE PUBLICATION.** Collected papers from scientific and technical conferences, symposia, seminars, or other meetings sponsored or cosponsored by NASA.
- **SPECIAL PUBLICATION.** Scientific, technical, or historical information from NASA programs, projects, and missions, often concerned with subjects having substantial public interest.
- **TECHNICAL TRANSLATION.** English-language translations of foreign scientific and technical material pertinent to NASA's mission.

Specialized services that complement the STI Program Office's diverse offerings include creating custom thesauri, building customized data bases, organizing and publishing research results . . . even providing videos.

For more information about the NASA STI Program Office, see the following:

- Access the NASA STI Program Home Page at <http://www.sti.nasa.gov>
- E-mail your question via the Internet to help@sti.nasa.gov
- Fax your question to the NASA Access Help Desk at (301) 621-0134
- Telephone the NASA Access Help Desk at (301) 621-0390
- Write to:
NASA Access Help Desk
NASA Center for Aerospace Information
7121 Standard Drive
Hanover, MD 21076



Tensile Properties and Microstructural Characterization of Hi-Nicalon SiC/RBSN Composites

Ramakrishna T. Bhatt
U.S. Army Research Laboratory, Lewis Research Center, Cleveland, Ohio

Prepared for
CIMTEC '98
9th International Conference on Modern Materials & Technologies
cosponsored by the Commission of the European Communities DG XII
and Gruppoo Colorobbia
Florence, Italy, June 14–19, 1998

National Aeronautics and
Space Administration

Lewis Research Center

Acknowledgments

I would like to thank Dr. Jeffrey Eldridge for performing interfacial shear strength measurements and T.A. Leonhardt for preparing the ceramographic specimens.

Available from

NASA Center for Aerospace Information
7121 Standard Drive
Hanover, MD 21076
Price Code: A03

National Technical Information Service
5285 Port Royal Road
Springfield, VA 22100
Price Code: A03

TENSILE PROPERTIES AND MICROSTRUCTURAL CHARACTERIZATION OF Hi-NICALON SiC/RBSN COMPOSITES

Ramakrishna T. Bhatt

NASA Lewis Research Center
21000 Brookpark Road
Cleveland, Ohio 44135

The room temperature physical and mechanical properties of silicon carbide fiber-reinforced reaction-bonded silicon nitride matrix composites (SiC/RBSN) were measured, and the composite microstructure was analyzed. The composites consist of nearly 24 vol% of aligned Hi-Nicalon SiC fiber yarns in a ~30 vol% porous silicon nitride matrix. The fiber yarns were coated by chemical vapor deposition with a 0.8 μm layer of boron nitride (BN) followed by a 0.2 μm layer of SiC. In the as-fabricated condition, both 1-D and 2-D composites exhibited high strength and graceful failure, and showed improved properties when compared with unreinforced matrix of comparable density. No indication of reaction between the SiC fiber and BN coating was noticed, but the outer SiC layer reacted locally with the nitridation enhancing additive in the RBSN matrix. A comparison is made between the predicted and measured values of matrix cracking strength.

1. INTRODUCTION

Reaction-bonded silicon nitride (RBSN) has long been considered a candidate material for hot section structural components in advanced heat engine applications^{1,2}. The main attributes of RBSN are ease of fabrication, near net shape capability, high creep resistance, high-temperature strength, and low density. In spite of these advantages, RBSN is not used for commercial applications because of its low fracture strength and fracture toughness at room temperature, and high internal oxidation rates between 800 and 1000°C. Although its strength properties can be improved by controlling the processing variables or by post-fabrication treatments³, and its internal oxidation problems can be alleviated by chemically vapor depositing a dense layer of Si_3N_4 or by infiltrating the porous body with a Si_3N_4 -yielding polymer^{4,5}, its fracture toughness cannot be altered to any perceptible degree by conventional processing methods. A solution to this problem is to reinforce the RBSN with high modulus, high strength ceramic fibers. Previous studies have shown that strong and tough SiC/RBSN composites can be fabricated by reinforcing RBSN with 144- μm -diameter SiC fibers⁶. Although this composite has been used as a model system to study structure and property correlation, it cannot be used for high-temperature applications for two reasons: (1) it has limited shape capability because the large diameter fibers cannot be bent to a radius less than 12 mm and (2) it is prohibitively expensive to machine complex-shaped components from a composite block. Both of these problems can be overcome by choosing small diameter ($\approx 14 \mu\text{m}$) SiC fibers as reinforcement.

Polymer derived small diameter SiC fibers such as CG Nicalon and Tyrranno fibers that were coated with a thin layer ($\sim 1 \mu\text{m}$) of carbon or BN have been explored earlier as reinforcement for RBSN⁷⁻⁹. Although in most cases limited strain capability beyond matrix fracture was

demonstrated, the ultimate fracture strength was low because of strength degradation of the fibers during high temperature nitridation. In recent years second generation small diameter SiC fibers such as Hi-Nicalon, Hi-Nicalon-S, and Sylramic fibers with better thermal stability than the first generation SiC fibers have been developed^{10, 11}. In a recent investigation, Bhatt and Hull¹² studied strength properties of coated Hi-Nicalon SiC fiber/RBSN tow composites processed under RBSN processing conditions. Fiber coatings were either pyrolytic boron nitride (PBN), PBN/Si-rich PBN, or boron nitride (BN)/SiC. This study concluded that all three CVD coated Hi-Nicalon SiC fibers are stable through the RBSN processing condition, but BN/SiC coated tow composites yielded greater strength retention than the other two tow composites.

The objectives of this study were to fabricate BN/SiC coated Hi-Nicalon SiC/RBSN composites, and to evaluate its room temperature mechanical properties and characterize its microstructure.

2. EXPERIMENTAL

2.1. Materials

The SiC fiber yarn (Hi-Nicalon) required for composite fabrication was procured from Dow Corning Corporation, Midland, MI. A typical fiber yarn contained 500 filaments. The supplier provided information indicates that the diameter of individual filaments in the yarn varies from 8 to 16 μm , and the average filament diameter is $\sim 14 \mu\text{m}$. The as-received fiber yarn had a polyvinyl acetate sizing. The as-received fiber yarns were coated with a dual layer system of $\sim 0.8 \mu\text{m}$ thick BN followed by $\sim 0.2 \mu\text{m}$ thick SiC. The coatings were applied by chemical vapor deposition (CVD) by 3M Corporation, Minneapolis, Minnesota.

2.2. Composite Fabrication

The silicon powder required for composite fabrication was obtained from Union Carbide Corporation, Linde Division, Tonawanda, New York. The as-received powder was mixed with a nitride enhancing additive, and the mixture was wet attrition milled in Stoddard solvent (a kerosene-based liquid) for 48h. Attrition milling was performed in a Si_3N_4 vessel using Si_3N_4 grinding media and a procedure similar to that used by Herbell et al¹³. Attrition milling reduced the particle size of silicon powder from 23 μm to 0.42 μm . The attrition milled silicon powder was dried in an oven maintained at 400⁰C in vacuum for 24h. The dried powder was stored in a glove chamber until further use.

Composites were fabricated by hot pressing a lay-up of silicon coated fiber mats to produce a SiC/Si preform and then nitriding the preform at high temperature in nitrogen. Details of the fabrication are reported by Bhatt and Babuder¹⁴. Here salient features of the composite fabrication will be described. In the first step, a silicon slurry was prepared by ball milling appropriate amounts of attrition milled silicon powder, a polymer binder, a dispersant, and a solvent. The required amount of the slurry was poured into a slurry tank. In the second step, the Hi-Nicalon SiC fiber tow was passed through a series of rollers to spread the tows and then into the tank filled with silicon slurry. The slurry coated fiber tows were wound on a metal drum at a desired spacing to prepare 150 mm wide fiber mat. After drying in air, the fiber mat was removed from the drum, and cut into 150 mm x 150 mm pieces. The cut mat was coated with a 0.5 mm

layer of silicon slurry by using a doctor blade apparatus. The composition of the slurry is similar to that used for the fiber coating. When dried, the mats were cut into 12 mm wide strips; some mats were cut parallel and others were cut transverse to the fibers. In the third step, eleven strips all unidirectional, or alternate strips of unidirectional and transverse fiber lay-up were stacked in a stainless steel die and pre-pressed at room temperature. The pre-pressed tapes were hot pressed at 40 MPa at 800°C for 15 min to obtain a SiC/Si preform. Subsequently the preform was nitrided in a tube furnace using an appropriate nitridation cycle to convert silicon to silicon nitride matrix. The final dimensions of the specimens after nitriding were 150 mm x 12 mm x 2.5 mm.

2.3. Specimen Preparation and Testing

The composite panels were surface ground with a diamond particle impregnated metal bonded grinding wheel to remove excess matrix layer present on the surface.

For tensile testing, dog-bone shaped specimens were machined from the composite block by using an ultrasonic SiC slurry impact machine. At each specimen end, two glass fiber-reinforced epoxy tabs of dimension 37 mm x 12 mm x 1 mm were bonded, leaving ~60 mm for the gauge section. A wire wound strain gauge was bonded at the center of the gauge section to monitor the strain during the tensile test. The specimens were tested at room temperature until failure in a servo-controlled tensile testing machine equipped with self aligning grips at a cross-head speed of 1.3 mm/min. Three to five specimens were tested to generate tensile data.

For microstructural examination, some composite specimens were sectioned normal to the fibers, mounted in a metallographic mold, ground successively on 40 μm down to 3 μm diamond particle impregnated metal disks, and polished in a vibratory polisher on a micro cloth using a 0.3 μm diamond powder paste. The mounted specimens were coated with a thin layer of carbon or palladium in a vacuum evaporator to avoid charging during observation in a scanning electron microscope (SEM).

Cyclic fiber push-in tests were performed using a desktop fiber push-out apparatus equipped with capacitance gauges for displacement measurements as previously described¹⁵. The Hi-Nicalon SiC fibers were pushed-in using a 70°-included-angle conical diamond indenter with a 10 μm diameter flat on the bottom. To prevent the sides of the conical indenter from indenting the matrix, the push-in distances were restricted to just a couple of microns.

3. RESULTS AND DISCUSSION

3.1. Physical Properties

The room temperature apparent and skeletal densities were measured to estimate % open porosity in SiC/RBSN composite specimens. The skeletal density was measured by Archimedes method using methylethylketone liquid. The measured data are tabulated in Table I. The data represent an average of five specimens.

Table I. Summary of physical property data for Hi-Nicalon SiC/RBSN composites.

Fiber lay up	Fiber volume fraction, %	Apparent density, gm/cc	Porosity, vol %
0	24	1.96 ± 0.02	36 ± 5
0/90	24	1.94 ± 0.01	37 ± 5

3.2. Microstructure

The SEM photographs of the cross-section of 1-D CVD BN/SiC coated Hi-Nicalon SiC/RBSN composites are shown in Fig. 1. A low magnification photograph (Fig. 1(a)) reveals that silicon slurry, hence silicon nitride matrix, is well infiltrated between the filaments in the tows, but between the fiber tows distinct matrix rich regions can be found. Also the matrix is very porous with isolated large pores distributed throughout the cross-section. A higher magnification photograph of the cross-section of the yarn shows that the CVD interface coating on the Hi-Nicalon fibers is non-uniform and irregular (Fig.1(b)). Generally, the thickness of coating on the periphery of the tows was significantly greater than in the interior of the tows. Figure 1 (c) is a photograph of a single SiC filament showing the BN/SiC interface. The darker ring around the fiber is the BN coating and the grayish ring on top of the BN is the SiC coating. The BN coating appears to be uniform, but the SiC coating is generally nodular and rough. TEM analysis of the interface indicates (photographs not shown) that the BN coating is amorphous, and that the SiC coating is crystalline and composed of columnar grains. Figures 1(a) and (b) show that the majority of the RBSN matrix and SiC outer coating interface showed no reaction, but local areas of reaction are present. TEM revealed that the nitride enhancing additive in the RBSN matrix locally reacted with the SiC coating.




Figure 1. SEM photographs of a cross-section of 1-D BN/SiC coated Hi-Nicalon SiC/RBSN composites ($V_f \sim 0.24$).

3.3. Mechanical Behavior of Laminated Composites

Typical room temperature tensile stress-strain behaviors of $[0]_{10}$ and $[0/90]_8$ BN/SiC coated Hi-Nicalon SiC/RBSN composites (~ 24 vol%) are shown in Fig. 2. Included in the figure is the tensile stress-strain behavior of the monolithic RBSN matrix fabricated under similar conditions. The stress-strain curve of both 1-D and 2-D reinforced BN/SiC coated Hi-Nicalon SiC/RBSN composites showed two distinct regions: an initial linear region followed by a non-linear region. At ultimate load the composite specimens failed abruptly. In contrast, the stress-strain curve of monolithic RBSN showed only one initial linear region. Also noticed is that the strain capability of both 1-D and 2-D composites is significantly greater than that of the monolithic RBSN. The tensile data are summarized in Table II. The data represent average of 3 to 5 tests.

Figure 3 shows the fracture surface of 1-D BN/SiC coated Hi-Nicalon SiC/RBSN composites. It is obvious from the figure that the composites exhibit a significant amount of fiber pull out, typical of a tough composite. Examination of the gage section of the fractured specimen indicates a concentration multiple matrix cracks near the main crack which caused fracture.




Figure 2. Typical room temperature tensile-strain curves for 1-D and 2-D BN/SiC coated Hi-Nicalon SiC/RBSN composites ($V_f \sim 0.24$).

Table II. Room temperature tensile property data for Hi-Nicalon SiC/RBSN composites.

Material	Fiber layup	Fiber volume fraction, %	Proportional limit stress, MPa	Proportional limit strain, %	Elastic modulus, GPa	Ultimate tensile strength, MPa	Ultimate tensile strain, %
RBSN	-	-	60	0.1	60	60	0.1
SiC/RBSN	0	24	298 \pm 13	0.27 \pm 0.01	110 \pm 4	343 \pm 24	0.35 \pm 0.04
SiC/RBSN	0/90	24	84 \pm 16	0.1 \pm 0.01	85 \pm 2	133 \pm 20	0.35 \pm 0.07




Figure 3. SEM photograph of the tensile fracture surface of a 1-D BN/SiC coated Hi-Nicalon SiC/RBSN composite ($V_f \sim 0.24$).

3.4. Interfacial Shear Strength

The room temperature load-displacement curve obtained from the push-in test for 1-D BN/SiC coated Hi-Nicalon SiC/RBSN composites is shown in Fig. 4. The data were analyzed by first subtracting the appropriate load-train compliance correction from the measured displacements. The fiber debond initiation stress was determined and the frictional sliding stresses was estimated. An estimate of frictional sliding stress, τ , was made using the constant τ model of Marshall and Oliver¹⁶ and the following relationship:

$$U = U_0 + F^2 / 8 \Pi^2 r^3 E_f \tau$$

where U is the fiber end displacement, U_0 is the residual fiber end displacement after the previous unloading, F is the applied load, r is the fiber radius, and E_f is the fiber modulus. In addition, a debond initiation stress, σ_d , could be calculated from the debond initiation load, F_d , (load at which fiber end begins to move by the relation $\sigma_d = F_d / \Pi r^2$). The values of measured debond and interfacial shear stresses for this composites are 1.4 GPa and 15.4 MPa respectively.




Figure 4. Typical room temperature fiber push-in test behavior of BN/SiC coated Hi-Nicalon SiC/RBSN composite.

3.5. Matrix Cracking Strength Prediction

A fiber bridging crack model developed by Aveston, Cooper, and Kelly¹⁷ was used to predict the matrix cracking strength in SiC/RBSN composites. For this calculation the following values of $E_f=270$ GPa, $E_m= 60$ GPa, Γ_m (matrix fracture energy) $=36$ J/m², $\alpha_f=3.8 \times 10^{-6}$, $\alpha_m=5.4 \times 10^{-6}$, $\tau = 15$ MPa, $\Delta T=1175$ and $R=7 \times 10^{-6}$ m were used. The variation of matrix cracking strength with fiber fraction was predicted with and without accounting for thermal residual stresses. Results are compared with the measured values in Fig. 5. The plot indicates that the predicted values are much higher than the measured values. The reasons for the difference are being investigated.




Figure 5. Experimental data and predictions of first matrix cracking stress by the long fiber-bridging crack model for SiC/RBSN composites.

4. CONCLUSIONS

A strong and tough RBSN can be fabricated by using BN/SiC coated Hi-Nicalon SiC fibers. Further improvement in composite properties are possible by controlling fiber fraction, and processing variables.

REFERENCES

- 1) F.L. Riley, Nitrogen Ceramics, (Noordhoff, Leyden, 1977).
- 2) E.M. Lenoe, R.N. Katz and J.J. Burke, Ceramics for High Performance Applications, Vol. III, (Plenum, New York, London, 1979).
- 3) J.A. Mangels and G.J. Tennenhouse, Bull. Am. Ceram. Soc. **59** [2] (1980) 1216.
- 4) O.J. Gregory and M.H. Richman, J. Amer. Ceram. Soc. **67** (1984) 335.
- 5) S. Kleber and J. H. Weiss, J. Euro. Ceram. Soc. **10** (1992) 205.
- 6) R.T. Bhatt, U.S. Patent No. 4689188 (1987).
- 7) J.W. Lucek, G.A. Rossetti, Jr., and S.D. Hartline, Stability of continuous Si-C(-O) reinforcing elements in reaction-bonded silicon nitride process environments, in: Metal Matrix, Carbon, and Ceramic Matrix Composites 1985, NASA CP-2406, ed. J.D. Buckley, NASA, Washington, D.C., 1985.
- 8) T.L. Starr, D.L. Mohr, W.J. Lackey, and J.A. Hanigofsky, Ceram. Eng. Sci. Proc., **14** [9-10] 1125-1132 (1993).
- 9) G.H. Woblewska and G. Ziegler, Ceramic Trans. **58**, 131-136 (1995).
- 10) M. Takeda, Y. Imai, H. Ichikawa, T. Isikawa, N. Kasai, T. Seguchi, and K. Okamura, Ceram. Eng. Sci. Proc., **13** (7-8), 209-217, (1992).
- 11) J.B. Hurst, D. Gorican, and H.M. Yun, Ceramic Trans. **58**, 131-136, (1995).
- 12) R.T. Bhatt and D.R. Hull, Effects of fiber coatings on tensile properties of Hi-Nicalon SiC/RBSN tow composites, NASA TM-113170, NASA, Washington, D.C. 1997.
- 13) T.P. Herbell, T.K. Glasgow and N.W. Orth, Bull. Amer. Ceram. Soc., **63** [9] (1984) 1176.
- 14) R.T. Bhatt and R. Babuder, Processing and properties of Hi-Nicalon SiC/RBSN composites, NASA TM (in press).
- 15) J.I. Eldridge, Desktop fiber push-out apparatus, NASA TM-105341, NASA, Washington, D.C., 1991.
- 16) D.B. Marshall and W.C. Oliver, Mater. Sci. Eng. A, **126**, 95-103 (1990).
- 17) J. Aveston, G. Cooper, and A. Kelly, Single and multiple fracture, in: The Properties of Fiber Composites (Conference Proceedings, National Physical Laboratory, Guildford) IPC Science and Technology Press Ltd., 1971.

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE October 1998		3. REPORT TYPE AND DATES COVERED Technical Memorandum
4. TITLE AND SUBTITLE Tensile Properties and Microstructural Characterization of Hi-Nicalon SiC/RBSN Composites			5. FUNDING NUMBERS WU-505-63-12-00 1L162211A47A	
6. AUTHOR(S) Ramakrishna T. Bhatt				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) NASA Lewis Research Center Cleveland, Ohio 44135-3191 and U.S. Army Research Laboratory Cleveland, Ohio 44135-3191			8. PERFORMING ORGANIZATION REPORT NUMBER E-11379	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) National Aeronautics and Space Administration Washington, DC 20546-0001 and U.S. Army Research Laboratory Adelphi, Maryland 20783-1145			10. SPONSORING/MONITORING AGENCY REPORT NUMBER NASA TM-1998-208657 ARL-TR-1791	
11. SUPPLEMENTARY NOTES Prepared for CIMTEC '98, 9th International Conference on Modern Materials & Technologies, cosponsored by the Commission of the European Communities DG XII and Gruppo Colorobbia, Florence, Italy, June 14-19, 1998. Responsible person, Ramakrishna T. Bhatt, organization code 0330, (216) 433-5513.				
12a. DISTRIBUTION/AVAILABILITY STATEMENT Unclassified - Unlimited Subject Category: 27 This publication is available from the NASA Center for AeroSpace Information, (301) 621-0390.			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) The room temperature physical and mechanical properties of silicon carbide fiber-reinforced reaction-bonded silicon nitride matrix composites (SiC/RBSN) were measured, and the composite microstructure was analyzed. The composites consist of nearly 24 vol% of aligned Hi-Nicalon SiC fiber yarns in a ~30 vol% porous silicon nitride matrix. The fiber yarns were coated by chemical vapor deposition with a 0.8 mm layer of boron nitride (BN) followed by a 0.2 mm layer of SiC. In the as-fabricated condition, both 1-D and 2-D composites exhibited high strength and graceful failure, and showed improved properties when compared with unreinforced matrix of comparable density. No indication of reaction between the SiC fiber and BN coating was noticed, but the outer SiC layer reacted locally with the nitridation enhancing additive in the RBSN matrix. A comparison is made between the predicted and measured values of matrix cracking strength.				
14. SUBJECT TERMS Properties; Microstructure; SiC/RBSN; Hi-Nicalon			15. NUMBER OF PAGES 15	
			16. PRICE CODE A03	
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT	